

Telefon-Nr. 0271/319923
Telefax-Nr. 0271/3199244

Specification Sheet NK 20

Basis:	NR / SBR
Cell structure:	closed
Water assimilation	app. 3 – 6 %
Density:	app. 130 – 160 kg/m ³
Degree of hardness:	RE 41/42
Compression-Deflection:	app. 20 %
Temperature range:	app. + 80° C
Lowest temperature range:	app. - 25° C
Flammability:	easily flammable
Resistance against:	
Oil + Fat	not resistant
Acids	not resistant
Abrasion:	slight

Differing porosity and surface-structure as well as differing chemical and technological knowledge are subject to proviso. All technical values are tested with best possible thoroughness. No responsibility is accepted for the correctness of this information.

With cellular material shrinkage is commercial and unavoidable.